



4035 rue Lavoisier  
Boisbriand, QC  
J7H 1N1

Tel: 1 800 263-1450  
(450) 434-2744  
Fax: 1 800 465-6039  
(450) 434-5998

220 Pony Drive Unit 1A  
Newmarket, ON  
L3Y 7B6

Tel: 1 800 263-1450  
(905) 898-1139  
Fax: 1 800 465-6039  
(905) 898-1004

## SPECIFICATION SHEET

### PVC

Ref. Part: ES28-110-P60

PHYSICAL PROPERTIES	RESULTS
<b>HARDNESS</b> , Shore A, 15 seconds	62
<b>SPECIFIC GRAVITY</b>	1.26
<b>TENSILE STRENGTH</b> , psi	1,389
<b>ULTIMATE ELONGATION</b> , %	386
<b>VOLATILE LOSS</b> , % weight loss 24 hrs @ 405°C	1.15

*\*\*Information obtained herein is based on data, which we believe to be reliable. Seeing as this compound may be used in many different and use applications, alone, or in conjunction with other products, we cannot guarantee the same results will be obtained. It is recommended that each user make their own tests to determine the suitability and/or performance acceptance of this material for their particular application.\*\**