



TYPICAL PROPERTIES

Reference Document No. GTS-3300S

Compound No./Material Name:	Material Description:	Manufacturing Method:
ARLON® 3000 XT	Enhanced PEEK	Injection Molded

DESCRIPTION (ASTM Standards)	TYPICAL					
Physical & Mechanical Properties	Arlon® 3000 XT			PEEK		
Color	Black			Tan		
Specific Gravity (D792)	1.29			1.30		
Hardness, Shore D, Points (D2240)	88			87		
Izod Impact, Notched, ft-lbf/in [J/m] (D4812)	1.64 [87.6]			1.38 [73.7]		
Izod Impact, Unnotched, ft-lbf/in [J/m] (D256)	37.8 [2,018.5]			no break		
Water Absorption @ 24 Hrs., Change in weight, % (D570)	0.09			0.07		
Coefficient of Friction Dynamic, PV=5000 psi-ft/min (D3702)	0.60			0.56		
Wear Factor (PV=5000 psi-ft/min), $\times 10^{-10}$ in ³ min/(ft-lb-hr) (D3702)	110.6			451.4		
Heat Deflection Temperature @ 264 psi (1.83 MPa), °F [°C] (D648)	>572 [>300]			338 [170]		
DSC, Melting Point (Tm), °F [°C] (D3418)	665 [352]			649 [343]		
Temperature Properties	75°F (23°C)	392°F (200°C)	500°F (260°C)	75°F (23°C)	392°F (200°C)	500°F (260°C)
Tensile Yield Strength, psi [MPa] (D638-Type1)	17,100 [117.90]	4,820 [33.23]	3,820 [28.27]	14,900 [102.73]	4,200 [28.96]	2,600 [17.93]
Tensile Strength at Break, psi [MPa] (D638-Type1)	16,900 [116.50]	7,620 [52.54]	5,380 [37.09]	14,100 [97.22]	6,300 [43.44]	6,100 [42.06]
Elongation at Break, % (D638-Type1)	8–15	>25	>25	25–35	>40	>40
Tensile Modulus, psi [MPa] (D638-Type1)	559,000 [3,854.17]	175,160 [1,207.69]	88,100 [607.43]	595,000 [4,102.4]	57,300 [395.07]	38,700 [266.83]
Flexural Strength at 5% Strain, psi [MPa] (D790)	23,300 [160.65]	5,880 [40.54]	3,740 [25.79]	25,700 [177.20]	3,400 [23.44]	2,300 [15.86]
Flexural Modulus, psi [MPa] (D790)	628,000 [4,329.91]	158,000 [1,089.37]	90,200 [621.91]	654,000 [4,509.17]	76,000 [524.00]	50,300 [346.81]
Compressive Strength, psi [MPa] (D695)	22,000 [151.68]	10,300 [71.02]	5,500 [37.92]	19,900 [137.21]	4,080 [28.13]	2,590 [17.86]
Compressive Modulus, psi [MPa] (D695)	525,000 [3,619.75]	226,000 [1,558.22]	132,000 [910.11]	592,200 [4,083.08]	75,200 [518.49]	16,900 [116.52]
Shear Strength (test performed on flex bars), psi [MPa] (D732)	15,300 [105.49]	9,050 [62.40]	6,880 [47.44]	12,700 [87.56]	4,100 [28.27]	3,300 [22.75]

typical properties / arlon® 3000 xt

© 2014, Greene, Tweed all rights reserved
All trademarks are property of their respective owners.
06/14-GT DS-US-GE-194

TYPICAL PROPERTIES

Reference Document No. GTS-3300S

Compound No./Material Name:

ARLON® 3000 XT

Material Description:

Enhanced PEEK

Manufacturing Method:

Injection Molded

DESCRIPTION (ASTM Standards)	TYPICAL					
Thermal Properties	Arlon® 3000 XT			PEEK		
Coefficient of Thermal Expansion (Axial), $\mu\text{m}/(\text{m}^\circ\text{C})$ (E831)	55.4 (T<T _g), 120 (T>T _g)			46.8 (T<T _g), 135 (T>T _g)		
Electrical Properties	Arlon 3000 XT			PEK		
	257°F (125°C)	392°F (200°C)	527°F (275°C)	257°F (125°C)	392°F (200°C)	527°F (275°C)
Volume Resistivity at High Temperature**, $\times 10^{15}$ Ohm-cm (D257)	4.85	0.88	0.71	3.82	0.83	0.75
Surface Resistivity at High Temperature**, $\times 10^{14}$ Ohm-cm (D257)	8.20	1.30	0.97	5.61	1.22	0.96
Dielectric Strength, kV/mil, thickness = 40 mil (D149)	15.2			15.4		

Note

** Tests performed with flex bars.

Unless otherwise noted, all tests performed on ASTM standard samples.

Arlon 3000 XT is patent pending. Arlon® 3000 XT by Greene, Tweed based on VESTAKEEP®, an Evonik product



Contact Us

Greene, Tweed
Kulpsville, PA, USA

Tel: +1.215.256.9521
Fax: +1.215.256.0189

www.gtweed.com

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.