

Cali Bamboo 9365 Waples Street Suite D San Diego, CA 92121 USA

Report Date: 12/20/2013 Project #: 0721341 Report Of: CARB OQA Sample Report #: 0721341-44 Sample #: 6820 Benchmark Holdings, LLC Reporting 2710 West 5th Avenue, Eugene, OR 97402 USA Phone:541/484-9212 - Fax: 541/344-2735

CARB OQA Sample

Chamber Results			
	Impinger		
	#1		
Observed Flow Rate (I/m):	1.000		
Corr. Vol. of Air Sample:	30.552		
Raw Absorbance Values:	0.000		
PROFESSION AND STREET	0.001		
	0.000		
Average Absorbance:	0.000		
Unadjusted PPM:	0.000		
Temp. Correction Factor 77°F:	0.97		
R.H. Correction Factor 50% RH:	1.03		
Standardized Concentration PPM:	0.000		
Maximum PPM: Pha	se 2 = 0.05		

Formaldahyde Emissions Using Small Chamber							
	Production Data						
	Product:	Product: Sample 29 70.03.WIDEFNAT.56.B					
	Supplier:	NS	Prod Date:	NS			
	Prod Group:	*	Control Date:	NS			
	Test Date:	19-Dec-13	Coll. Date:	NS			

CHAMBER ID#:	2				
Chamber Conditions					
Barometric Pressure (in):	30.50				
Dry Bulb Temp (°F):	77.50				
Relative Humidity (%):	48.70				
Length of Test (minutes):	30.00				

on Detectable

Sample passes CARB Phase 2 standard. *Product is Bamboo flooring. Loading Comments: ratio/requirements for HWPW were used for a worst-case scenario.

Parameters:							
Loading Ratio:	0.430	Volume =	.1191863m³				
Chamber Dimensions:	.49213m x .49213m x .49213m						
Air Exchange Rate:	0.50 ± 0.05 air changes per hour		8				

^{*}The chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute at 30 ±2 minutes.

*This report has been produced for the exclusive use of: Cali Bamboo (client), and may not be reproduced except in its entirety, and only with the expressed, written approval of BMI. No one other than BMI's client shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.

ACCREDITED

Respectfully Submitted,

Benchmark Holdings LLC

Travis R. Snapp Managing Director / COO Benchmark International LLC

^{*}The samples were conditioned for seven days prior to testing at 70° to 80° F and 45% to 55% relative humidity. During conditioning, the formaldehyde background level was 0.01 parts per million or less.

^{*}Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and restraints. No warranty, expressed or implied, is made.